



Technical data

Material		
Backing	PP backing fleece, PP copolymer special membrane	
Adhesive	Modified water-resistant SOLID adhesive	
Release film	Single/double-split silicone-coated PE sheet	

Property	Regulation	Value
Colour		White
sd value	EN 1931	2.8 m
g value		14 MN·s/g
Vapour permeance	ASTM E 96	1.17 US perms
Airtightness	ift, MO-01/1:2007-01, Abs. 5	Up to 1000 Pa, around window
Bond durability, non-aged/aged	DIN 4108-11	Passed
Can be plastered over		Yes
Installation temperature		Above -10 °C ; 14 °F
Temperature resistance		Permanent -40 °C to 90 °C ; -40 °F to 194 °F
Storage		Cool and dry

Areas of application

For interior airtight and vapour-checking joints between windows, doors or airtightness layers and adjacent building components made of wood or mineral substrates such as concrete and masonry, with full-surface adhesion. The modified water-resistant SOLID adhesive ensures quick and permanent joints with the subsurface. The taped joint is immediately airtight and can be subjected to loading. The fleece can simply be plastered over in accordance with the installation instructions.

Splits on release film

Tape width Split (approx.)

80 mm (3 1/8") 20 | 60 mm (7/8" | 2 3/8")
 100 mm (4") 20 | 40 | 40 mm (7/8" | 1 5/8" | 1 5/8")
 150 mm (5 7/8") 20 | 70 | 60 mm (3/4" | 2 3/4" | 2 3/8")
 200 mm (7 7/8") 20 | 100 | 80 mm (3/4" | 4" | 3 1/8")

Supply forms

Art. no.	GTIN	Length	Width	Splits on release film	Weight	Sales unit	Container
15431	4026639154316	30 m	80 mm	20 60 mm	0.975 kg	8	384
15432	4026639154323	30 m	100 mm	20 40 40 mm	1.2 kg	8	288
15433	4026639154330	30 m	150 mm	20 70 60 mm	1.8 kg	4	192
15434	4026639154347	30 m	200 mm	20 100 80 mm	2.4 kg	4	144

Advantages

- ✓ Saves time: the joint is immediately airtight and can be subjected to loading
- ✓ Can be plastered over directly: defined transition between window and/or vapour check and plasterwork
- ✓ Reliable joints: water-resistant SOLID adhesive has extremely strong adhesion on mineral substrates too
- ✓ Independently confirmed suitability: tests in accordance with MO-01/1 passed at IFT in Rosenheim, Germany
- ✓ Construction in adherence with standards: for airtight sealing in accordance with DIN 4108-7, SIA 180 and RE 2020
- ✓ Excellent values in hazardous substance testing, has been tested according to the ISO 16000 evaluation scheme

Substrates

Clean substrates before sticking. Uneven mineral substrates may need to be levelled with a smooth finish. Adhesion to frozen surfaces is not possible. There must be no water-repellent substances (e.g. grease or silicone) on surfaces where adhesives are to be applied. The width of the adhesive tape that is to be plastered over should generally not exceed 60 mm (2 3/8") or 50% of the soffit area. Detailed recommendations can be obtained from the relevant plaster producer. Substrates must be sufficiently dry and stable.

Permanent adhesion is achieved on all pro clima interior membranes and on other vapour check and airtight membranes (e.g. those made of PE, PA, PP and aluminium).


Adhesion can be carried out on planed and painted wood, hard plastics, hard wood-based panels (chipboard, OSB and plywood panels), metal (e.g. pipes, windows etc.), rigid foam insulation materials that can be plastered over, and on mineral substraces such as concrete and masonry.

The best results in terms of structural stability are achieved on high-quality substraces. It is your responsibility to check the suitability of the substrate; adhesion tests are recommended in certain cases. Pre-treatment with TESCON PRIMER is recommended in the case of substraces with insufficient stability.

General conditions

The bonds should not be subjected to tensile strain. Rub the adhesive tapes firmly to secure the adhesive bonds, taking care to ensure that there is sufficient resistance pressure behind them. Airtight seals can only be achieved if the sealing tape is installed free of folds and breaks. Ventilate regularly and systematically to prevent build-up of excessive humidity. Use a dryer if necessary.

When plastering, please observe the recommendations of the plaster manufacturer for non-absorbent substraces. A bonding course may be necessary.



Prüfbericht Nr. 16-000527-PROZ
(PB 1-E03-020310-de-01)
- CONTEGA SOLIDO SL
- CONTEGA SOLIDO EXO
nach MO-01/1:2007-01, Abs. 5
24.06.2016



*Information sur le niveau d'émission de substances volatiles dans l'air intérieur, présentant un risque de toxicité par inhalation, sur une échelle de classe allant de A+ (très faibles émissions) à C (fortes émissions)

Tested for hazardous substances according to



The information provided here is based on practical experience and the current state of knowledge. We reserve the right to make changes to the recommended designs and processing or to make alterations due to technical developments and associated improvements in the quality of our products. We would be happy to inform you of the current technical state of the art at the time you use our products.

Further information about installation and design details is available in the pro clima planning documentation. If you have any questions, please contact [pro clima Technical Support](<https://proclima.com/service/technical-support>).

MOLL

bauökologische Produkte GmbH
Rheinthalstraße 35 - 43
D-68723 Schwetzingen
Fon: +49 (0) 62 02 - 27 82.0
eMail: info@proclima.de